


TPT-0260


Tyvek® 1073B with SealScience® Adhesive



Attribute	Test Method	Typical Value (US)	Typical Value (Int'l)
PHYSICAL			
Substrate basis weight	ASTM D3776	45.8lbs/3000 ft ²	74.7 g/m ²
Adhesive coat weight	ASTM F2217	7.0 lbs/3000 ft ²	11.4 g/m ²
Total basis weight	—	52.8 lbs/3000 ft ²	86.1 g/m ²
Yield	Calculated	8,182 in ² /lb	11.6 m ² /kg
Thickness	ASTM F2251	7.3 mil	185 µm
MECHANICAL			
Tensile (MD)	EN ISO 1924	46 lb/in	205 N
Tensile (CD)	EN ISO 1924	49 lb/in	219 N
Elmendorf tear (MD)	ASTM D1424	0.70 lb	3.2 N
Elmendorf tear (CD)	ASTM D1424	0.90 lb	4.0 N
Mullen burst	EN ISO 2758	175 psi	1,207 kPa
PERMEATION			
Porosity—Gurley	TAPPI T460	<75 sec/100cc	—
Porosity—Bendtsen*	ISO-5636-3	—	>152 mL/min

This information describes typical product characteristics for customer evaluation. It is not intended to be a final specification or warranty of performance. Seal data generated in laboratory.

* Calculated value.



V5.2018 Note: Determination of the specific suitability of this product for individual applications is the sole responsibility of the purchaser. The information contained herein is correct to the best of our knowledge. Recommendations or suggestions are made without guarantee of representation as to results. Nothing in this disclosure of information shall be deemed by implication or otherwise to convey to the recipient of this information any rights under any patents, patent applications, trademarks, copyrights or invention owned by Oliver Products Company.

Oliver™, Ofilm®, Ofoil®, DurOfoil®, Xhale®, and SealScience® are registered trademarks of Oliver Products Company. Surlyn® and Tyvek® are E.I. DuPont Company registered trademarks.

Description

TPT-0260 is a heat sealable, adhesive coated, medical-grade packaging material. Tyvek® 1073B is an extremely strong, tear resistant, breathable substrate with excellent microbial barrier properties. The SealScience® adhesive creates clean peelable bonds with visual seal indication.

Typical Application

This product is compatible with ethylene oxide (EO) and gamma radiation sterilization. It seals to a variety of thermo-formable plastics, including PVC, Styrene, HIPS, PETG, Polyethylenes and certain grades of Polypropylene. It fluoresces under UV light for coating continuity examination.

Bio-compatibility

TPT-0260 has been proven to be non-cytotoxic. Testing was conducted in accordance with ASTM F 2475, standard guide for bio-compatibility evaluation of medical device packaging materials, which includes ISO 10993-5 in-vitro cytotoxicity testing. Results available upon request.

Adhesive Color

Adhesive coating is available in white.

Shelf Life

Accelerated aging studies conducted on this Oliver® product demonstrate a shelf stability of up to 10 years. Most packaging materials are designed for stability over long periods of time provided good storage and handling practices are exercised.

Storage Conditions

Keep product in original package. Product should be stored at ambient warehouse conditions.

Sealing Conditions

Optimum sealing conditions are highly dependent upon the materials being sealed, the equipment, and production rates. Our recommendation is to begin testing at 240°F (115°C), 1.5 seconds, 50 psi.

Note: Other designations for this product include ITP-150.

